

**AMENDMENTS TO THE CLAIMS**

**This listing of claims will replace all prior versions and listings of claims in the application:**

**LISTING OF CLAIMS:**

Claims 1-2 (canceled).

3. (previously presented): A corrosion resistant member comprising a base material sprayed with a corrosion resistant glass sprayed coating which is a zirconia silicate glass containing at least one element selected from the group consisting of elements of the group 3a of the periodic table of elements and which when expressed by an Si-Zr-group 3a three-component triangular diagram, has a composition such that the atomic ratio of the respective metal elements (Si:Zr:group 3a) falls within the range connecting respective points of (70:25:5), (70:10:20), (50:20:30), (30:40:30), (30:50:20) and (45:50:5).

4. (previously presented): A corrosion resistant member comprising a base material sprayed with a corrosion resistant glass sprayed coating which is a zirconia silicate glass containing at least one element selected from the group consisting of elements of the group 2a of the periodic table of elements and which when expressed by an Si-Zr-group 2a three-component triangular diagram, has a composition such that the atomic ratio of the respective metal elements (Si:Zr:group 2a) falls within the range connecting-respective points of (70:25:5), (45:25:30), (30:40:30), (30:50:20) and (50:45:5).

5. (previously presented): A corrosion resistant member comprising a base material sprayed with a corrosion resistant glass sprayed coating which is an aluminosilicate glass containing at least one element selected from the group consisting of elements of the group 3a of the periodic table of elements and which when expressed by an Si-Al-group 3a three-component triangular diagram, has a composition such that the atomic ratio of the respective metal elements (Si:Al:group 3a) falls within the range connecting respective points of (70:20:10), (50:20:30), (30:40:30), (30:50:20), (45:50:5) and (70:25:5), wherein an interlayer of an SiO<sub>2</sub>-containing glass sprayed coating is provided between the base material and the corrosion resistant glass sprayed coating.

6. (previously presented): The corrosion resistant member as claimed in claim 5, wherein an interface between the base material and the corrosion resistant glass sprayed coating, or any one of interfaces among the base material, the interlayer of an SiO<sub>2</sub>-containing glass sprayed coating and the corrosion resistant glass sprayed coating forms a molten layer resulting from mutual melting each other.

7. (previously presented): A corrosion resistant member comprising a base material sprayed with a corrosion resistant glass sprayed coating which is an aluminosilicate glass containing at least one element selected from the group consisting of elements of the group 3a of the periodic table of elements and which when expressed by an Si-Al-group 3a three-component triangular diagram, has a composition such that the atomic ratio of the respective metal elements (Si:Al:group 3a) falls within the range connecting respective points of (70:20:10), (50:20:30),

(30:40:30), (30:50:20), (45:50:5) and (70:25:5), wherein the corrosion resistant glass sprayed coating has a surface roughness Ra of from 0.01 to 5  $\mu\text{m}$ .

Claims 8-10 (canceled).

11. (previously presented): A corrosion resistant member comprising a base material sprayed with a corrosion resistant glass sprayed coating which is an aluminosilicate glass containing at least one element selected from the group consisting of elements of the group 3a of the periodic table of elements and which when expressed by an Si-Al-group 3a three-component triangular diagram, has a composition such that the atomic ratio of the respective metal elements (Si:Al:group 3a) falls within the range connecting respective points of (70:20:10), (50:20:30), (30:40:30), (30:50:20), (45:50:5) and (70:25:5), wherein a most superficial layer of the sprayed coating forms a spherical protruded layer in which the concentration of aluminum and elements of the group 3a is lower than that of an internal sprayed coating.

12. (previously presented): The corrosion resistant member as claimed in claim 3, wherein an interlayer of an  $\text{SiO}_2$ -containing glass sprayed coating is provided between the base material and the corrosion resistant glass sprayed coating.

13. (previously presented): The corrosion resistant member as claimed in claim 3, wherein an interface between the base material and the corrosion resistant glass sprayed coating, or any one of interfaces among the base material, the interlayer of an  $\text{SiO}_2$ -containing glass

sprayed coating and the corrosion resistant glass sprayed coating forms a molten layer resulting from mutual melting each other.

14. (previously presented): The corrosion resistant member as claimed in claim 3, wherein the corrosion resistant glass sprayed coating has a surface roughness Ra of from 0.01 to 5  $\mu\text{m}$ .

15. (previously presented): The corrosion resistant member according to claim 3, wherein a most superficial layer of the sprayed coating forms a spherical protruded layer in which the concentration of zirconium and elements of the group 3a is lower than that of an internal sprayed coating.

16. (previously presented): The corrosion resistant member as claimed in claim 4, wherein an interlayer of an  $\text{SiO}_2$ -containing glass sprayed coating is provided between the base material and the corrosion resistant glass sprayed coating.

17. (previously presented): The corrosion resistant member as claimed in claim 4, wherein an interface between the base material and the corrosion resistant glass sprayed coating, or any one of interfaces among the base material, the interlayer of an  $\text{SiO}_2$ -containing glass sprayed coating and the corrosion resistant glass sprayed coating forms a molten layer resulting from mutual melting each other.

18. (previously presented): The corrosion resistant member as claimed in claim 4, wherein the corrosion resistant glass sprayed coating has a surface roughness Ra of from 0.01 to 5  $\mu\text{m}$ .

19. (previously presented): The corrosion resistant member according to claim 4, wherein a most superficial layer of the sprayed coating forms a spherical protruded layer in which the concentration of zirconium and elements of the group 2a is lower than that of an internal sprayed coating.

Claims 20-21. (canceled).

22. (previously presented): A corrosion resistant member comprising a base material sprayed with a corrosion resistant glass sprayed coating which is an aluminosilicate glass or zirconia silicate glass containing at least one element selected from the group consisting of the group 2a, group 3a and group 4a of the periodic table of elements,

wherein a most superficial layer of the sprayed coating forms a spherical protruded layer in which the concentration of at least one of aluminum or zirconium and elements of the group 2a, group 3a and group 4a is lower than that of an internal sprayed coating.